

TAMPA STRIPE Serisi



1478



1520



1575



1586



QUALITY

Product Definition	ISO 2424	Tufted Loop Pile 1/10"
Gauge		
No. of Tufts	ISO 1763	± 168000/m ² (163043/ycd ²)
Pile Fibre	ISO 2424	100% Polypropylene
Pile Weight	ISO 8543	360 gr/m ² ± 5% (± 10 oz/ycd ²)
Pile Height	ISO 1765	3.0 mm ± 5%
Primary Backing	ISO 2424	PA/PES non-woven
Tile Backing		Polyex non-woven fabric
Total Thickness	ISO 1765	6.0 mm ± 5%
Total Weight	ISO 8543	3790 gr/m ² ± 7.5% (± 109 oz/ycd ²)
Tile Size	EN 986	50 x 50 cm (± 19.7" x 19.7")
Tiles per box		20
Use Classification	EN 1307	Light Contract Class 22
Abrasion		Pass
Vettermann Test	ISO 10361	Pass
Dimensional Stability	ISO 10361	Pass
Thermal Isolation		0.10 m ² K/W

ELEKTROSTATIC PROPERTIES

Static Loading	ISO 2424	Anti-static
Flame Properties		
Reaction to Fire	ISO 1763	
Hot Metal Nut Test	EN130501-1	CF-SI
		Low Radius

COLOUR FASTNESS PROPERTIES

Light		4.4
Rubbing, Dry	ISO 105 B02	5.0
Rubbing, Wet	ISO 105 X12	5.0
Shampoo		4.8
Water	ISO 105 E01	4.8

GENERAL

Recommended Maintenance	
Pile Direction	
Laying Instructions	

Test results are obtained when observed with a dry spectro-metric. Electrical charges are printed on the back of each tile. Best results are obtained when laid on a concrete floor. This requires an underlayment, grouting or leveling and may be laid loose on a flat, dry, non-slippery floor. When there are laid on carpet, vinyl or in open areas longer than 10 m² it is advisable to use suitable roller rollers type on every 200 m² or so.

